

UMORE



LECCE
PORCELAIN TILES




12X24 TILE



SILVER
UMOSILVLEC1224M



LIGHT SILVER
UMOLISILEC1224M




KHAKI
UMOKHAKLEC1224M

24X24 TILE



SILVER
UMOSILVLEC2424M




LIGHT SILVER
UMOLISILEC2424M



KHAKI
UMOKHAKLEC2424M


12X12 SQUARE MOSAIC



SILVER
UMOSILVLEC25QM



LIGHT SILVER
UMOLISILEC25QM



KHAKI
UMOKHAKLEC25QM

SIZES

	Nominal Size	Actual Size	Thickness	Color	Finish	Sq. Ft. / Carton	Pcs / Carton
	12"x24"	11.60"x23.50"	8.5mm	Silver, Light Silver, Khaki	Matte	15.52 sqft	8
	24x24	23.50"x23.50"	9.5mm	Silver, Light Silver, Khaki	Matte	15.48 sqft	4
	12"x12" Square Mosaic	11.70"x11.70" Sheet 2"x2" Chip	8.5mm	Silver, Light Silver, Khaki	Matte	n/a	8

PRODUCT INFORMATION

Material	Porcelain
Body Color	Color Body
Edge	Rectified
Manufacturing Process	Inkjet
Country of Origin	USA

INSTALLATION

Suggested Grout Line Size 1/16", 1/8", or 3/16"

Installation Options	Floor/Wall
Shade Variation	V2 Slight Variation



PERFORMANCE PROPERTIES

Test	Test Standard	Result
Dynamic Coefficient of Friction	ANSI A137.1-2012 AcuTest™ ANSI/NFSI B101.3-2012	≥0.42
Water Absorption	ASTM C373-16 ISO 10545-3	≤0.5% (Impervious)
PEI Rating	ASTM C1027-09 or ISO 10545-7 (Glazed); ASTM C1243-93 (2015) or ISO 10545-6 (Unglazed)	3
Mohs Scratch Hardness	1:Talc 2:Gypsum 3:Calcite 4:Fluorite 5:Apatite 6:Feldspar 7:Quartz 8:Topaz 9:Corundum 10:Diamond	7
Breaking Strength	ASTM C648-04 (2014): ≥275 lbf	>275
Chemical Resistance	ASTM C650	Class A- 0
Freeze Thaw	ASTM C1026	Resistant

APPLICATION

Backsplash	✓	Indoor Wall	✓
Shower Wall	✓	Indoor Floor	✓
Shower Floor	✓	Pool Decking	✓
Submerged (Tub)	✓	Submerged (Pool)	✓
Outdoor	✓	Residential/Commercial Use:	✓

NOTES

Product specifications are subject to variation and tolerances within testing or productions and may vary. Variations in appearance, texture, construction, dimensions, performance, and style may occur and should be considered in product selection.

The product specifications listed reflect data from the manufacturer or from laboratory testing performed under specific testing conditions. As such it does not represent all conditions under which the products may be used or subjected.

For information on performance standards and/or suitability please consult the ANSI, ASTM, or Tile Council of North America resources.

