

# UMORE



PALERMO  
PORCELAIN TILES



12X24 TILE



SLATE  
UMOSLATPAL1224M



LIGHT SLATE  
UMOLISLPAL1224M



HAZELWOOD  
UMOHAZEPAL1224M




SEPIA  
UMOSEPIPAL1224M

12X12 RECTANGLE STACKED MOSAIC




SLATE  
UMOSLATPALSTKM



LIGHT SLATE  
UMOLISLPALSTKM





HAZELWOOD  
UMOHAZEPALSTKM



SEPIA  
UMOSEPIPALSTKM

### SIZES

	Nominal Size	Actual Size	Thickness	Color	Finish	Sq. Ft. / Carton	Pcs / Carton
	12"x24"	11.90"x24"	9mm	Slate, Light Slate, Hazelwood, Sepia	Matte	15.50 sqft	8
	12"x12" Rectangle Stacked Mosaic	12.12"x12.12" Sheet 2"x6" Chip	9mm	Slate, Light Slate, Hazelwood, Sepia	Matte	10.76 sqft	11

### PRODUCT INFORMATION

Material	Porcelain
Body Color	Standard
Edge	Rectified
Manufacturing Process	Inkjet
Country of Origin	Malaysia

### INSTALLATION

Suggested Grout Line Size	1/16", 1/8", or 3/16"
Installation Options	Floor/Wall
Shade Variation	V2 Slight Variation



### PERFORMANCE PROPERTIES

Test	Test Standard	Result
Dynamic Coefficient of Friction	ANSI A137.1-2012 AcuTest™ ANSI/NFSI B101.3-2012	>0.42
Water Absorption	ASTM C373-16 ISO 10545-3	<0.15%
PEI Rating	ASTM C1027-09 or ISO 10545-7 (Glazed); ASTM C1243-93 (2015) or ISO 10545-6 (Unglazed)	3
Mohs Scratch Hardness	1:Talc 2:Gypsum 3:Calcite 4:Fluorite 5:Apatite 6:Feldspar 7:Quartz 8:Topaz 9:Corundum 10:Diamond	6
Breaking Strength	ASTM C648-04 (2014): ≥275 lbf	≥275 lbf
Chemical Resistance	ASTM C650	Class 3
Freeze Thaw	ASTM C1026	Resistant

### APPLICATION

Backsplash	✓	Indoor Wall	✓
Shower Wall	✓	Indoor Floor	✓
Shower Floor	✓	Pool Decking	✗
Submerged (Tub)	✓	Submerged (Pool)	✗
Outdoor	✓	Residential/Commercial Use:	✓

### NOTES

Product specifications are subject to variation and tolerances within testing or productions and may vary. Variations in appearance, texture, construction, dimensions, performance, and style may occur and should be considered in product selection.

The product specifications listed reflect data from the manufacturer or from laboratory testing performed under specific testing conditions. As such it does not represent all conditions under which the products may be used or subjected.

For information on performance standards and/or suitability please consult the ANSI, ASTM, or Tile Council of North America resources.

