


UMORE




RHO
PORCELAIN TILES



12X24 TILE



WHITE
UMOWHTRHO1224M




BEIGE
UMOBEGRHO1224M




SHADOW
UMOSHADRHO1224M


24X24 TILE



WHITE
UMOWHTRHO2424M




BEIGE
UMOBEGRHO2424M




SHADOW
UMOSHADRHO2424M


12X12 SQUARE MOSAIC



WHITE
UMOWHTRHO2SQM



BEIGE
UMOBEGRHO2SQM



SHADOW
UMOSHADRHO2SQM

SIZES

	Nominal Size	Actual Size	Thickness	Color	Finish	Sq. Ft. / Carton	Pcs / Carton
	12"x24"	11.60"x23.50"	9.5mm	White, Beige, Shadow	Matte	15.52 sqft	8
	24x24	23.50"x23.50"	9.5mm	White, Beige, Shadow	Matte	15.48 sqft	4
	12"x12" Square Mosaic	11.70"x11.70" Sheet 2"x2" Chip	9.5mm	White, Beige, Shadow	Matte	n/a	8

PRODUCT INFORMATION

Material	Porcelain
Body Color	Color Body
Edge	Rectified
Manufacturing Process	Inkjet
Country of Origin	USA

INSTALLATION

Suggested Grout Line Size 1/16", 1/8", or 3/16"

Installation Options	Floor/Wall
Shade Variation	V1 Uniform Appearance



PERFORMANCE PROPERTIES

Test	Test Standard	Result
Dynamic Coefficient of Friction	ANSI A137.1-2012 AcuTest™ ANSI/NFSI B101.3-2012	≥0.42
Water Absorption	ASTM C373-16 ISO 10545-3	≤0.5% (Impervious)
PEI Rating	ASTM C1027-09 or ISO 10545-7 (Glazed); ASTM C1243-93 (2015) or ISO 10545-6 (Unglazed)	3
Mohs Scratch Hardness	1:Talc 2:Gypsum 3:Calcite 4:Fluorite 5:Apatite 6:Feldspar 7:Quartz 8:Topaz 9:Corundum 10:Diamond	7
Breaking Strength	ASTM C648-04 (2014): ≥275 lbf	>275
Chemical Resistance	ASTM C650	Class A- 0
Freeze Thaw	ASTM C1026	Resistant

APPLICATION

Backsplash	✓	Indoor Wall	✓
Shower Wall	✓	Indoor Floor	✓
Shower Floor	✓	Pool Decking	✓
Submerged (Tub)	✓	Submerged (Pool)	✓
Outdoor	✓	Residential/Commercial Use:	✓

NOTES

Product specifications are subject to variation and tolerances within testing or productions and may vary. Variations in appearance, texture, construction, dimensions, performance, and style may occur and should be considered in product selection.

The product specifications listed reflect data from the manufacturer or from laboratory testing performed under specific testing conditions. As such it does not represent all conditions under which the products may be used or subjected.

For information on performance standards and/or suitability please consult the ANSI, ASTM, or Tile Council of North America resources.