

# UMORE



SIENA  
PORCELAIN TILES





## 12X24 TILE



OAT  
UMOOAT-SIE1224M



CONCRETE  
UMOCONCSIE1224M



CLOUD  
UMOCLOUSIE1224M




DARK CLOUD  
UMODACLSIE1224M

## 12X12 SQUARE MOSAIC



OAT  
UMOOAT-SIE25QM



CONCRETE  
UMOCONCSIE25QM





CLOUD  
UMOCLOUSIE25QM



DARK CLOUD  
UMODACLSIE25QM

### SIZES

	Nominal Size	Actual Size	Thickness	Color	Finish	Sq. Ft. / Carton	Pcs / Carton
	12"x24"	11.80"x23.60"	7mm	Oat, Concrete, Cloud, Dark Cloud	Matte	17.46 sqft	9
	12"x12" Square Mosaic	11.60"x11.60" Sheet 2"x2" Chip	7mm	Oat, Concrete, Cloud, Dark Cloud	Matte	n/a	10

### PRODUCT INFORMATION

Material	Porcelain
Body Color	Standard
Edge	Tile: Pressed Mosaic: Rectified
Manufacturing Process	Inkjet
Country of Origin	Malaysia

### INSTALLATION

**Suggested Grout Line Size** Tile: 1/8", 3/16", 3/8", or 1/4"  
Mosaic: 1/16", 1/8", or 3/16"

**Installation Options** Floor/Wall

**Shade Variation** V2  
Slight Variation



### PERFORMANCE PROPERTIES

Test	Test Standard	Result
Dynamic Coefficient of Friction	ANSI A137.1-2012 AcuTest™ ANSI/NFSI B101.3-2012	>0.42
Water Absorption	ASTM C373-16 ISO 10545-3	≤0.5% (Impervious)
PEI Rating	ASTM C1027-09 or ISO 10545-7 (Glazed); ASTM C1243-93 (2015) or ISO 10545-6 (Unglazed)	3
Mohs Scratch Hardness	1:Talc 2:Gypsum 3:Calcite 4:Fluorite 5:Apatite 6:Feldspar 7:Quartz 8:Topaz 9:Corundum 10:Diamond	6
Breaking Strength	ASTM C648-04 (2014): ≥275 lbf	≥275 lbf
Chemical Resistance	ASTM C650	Class 3
Freeze Thaw	ASTM C1026	Resistant

### APPLICATION

Backsplash	✓	Indoor Wall	✓
Shower Wall	✓	Indoor Floor	✓
Shower Floor	✓	Pool Decking	✓
Submerged (Tub)	✓	Submerged (Pool)	✓
Outdoor	✓	Residential/Commercial Use:	✓

### NOTES

Product specifications are subject to variation and tolerances within testing or productions and may vary. Variations in appearance, texture, construction, dimensions, performance, and style may occur and should be considered in product selection.

The product specifications listed reflect data from the manufacturer or from laboratory testing performed under specific testing conditions. As such it does not represent all conditions under which the products may be used or subjected.

For information on performance standards and/or suitability please consult the ANSI, ASTM, or Tile Council of North America resources.

